



APPLICATION

Power cable for battery energy storage systems and grids installations.

It can be buried or installed in a tube as well as outdoors without requiring additional protection and can withstand in damp conditions including total submersion in water (AD8).

Storaflex cables have good Oil and chemical resistance characteristics also excellent resistance to salt mist + chemical vapors.

CONSTRUCTION

Conductor	Electrolytic annealed flexible bare copper-Class 5 according to IEC 60228 (Class 2 and/or tinned copper available on request.)
Insulation	Hard Grade Ethylene Propylene Rubber, HEPR according to IEC 60502-1
Outer Sheath	Special Halogen Free Flame Retardant HFFR compound according to IEC 60502-1
Sheath Colour	Black (Other colours available upon request)

TECHNICAL CHARACTERISTICS

Rated Voltage (U ₀ /U)	600 / 1000 V AC 900 / 1500 V DC
Max Voltage U _{max}	1200 V AC 1800 V DC
Test Voltage	3,5 kV AC
Operating Ambient Temperature	-40°C / +90°C
Lowest Installation Temperature	-15°C
Max. Short Circuit Temperature	+250°C
Bending Radius	6 x Outer Diameter at fixed installed 10 x Outer Diameter during installation

DESIGN STANDARDS

Construction	IEC 60502-1
Flame Retardancy	IEC 60332-1-2
Halogen Content	IEC 60754 / 1-2
Smoke Emission	IEC 61034 / 1-2
Ozon Resistance	IEC60811 / 403
UV Resistance	EN 50618
CPR	EN 50575 (Eca)

CABLE MARKING

SOLEN CABLE STORAFLEX 1xN mm² 600/1000 V IEC 60502-1 IEC 60332-1-2 SCXXXX <CE> Eca (yyyy) XX MT

*N: Cross Section *SCXXXX: Traceability Code *(yyyy): Year marking *XX MT: Meter Marking



Eca

Customer:

Date:

Solen Kablo San. Tic. A.Ş.
Arap Cami Mah. Arapkayyum Sok.
Karavelioğlu Han No.23 / 5
Beyoğlu - 34420 İstanbul - Türkiye

All data given here is informative and subject to change.

© Solen Kablo, Türkiye 2024
www.solenkablo.com



DIMENSIONAL PARAMETERS

PART NO.	NUMBER OF CORES	CROSS SECTIONS mm ²	OVERALL DIAMETER mm	BENDING RADIUS (min.) mm	APP. WEIGHT kg/km	MAX. CONDUCTOR RESISTANCE (*) 20°C ohm/km
STORAFLEX	1	16	9,1 -0,3 /+0,5	54,6	187	1,21
STORAFLEX	1	25	10,7 -0,3 /+0,5	64,2	272	0,78
STORAFLEX	1	35	12,0 -0,3 /+0,5	72,0	375	0,554
STORAFLEX	1	50	13,6 -0,3 /+0,5	81,6	515	0,386
STORAFLEX	1	70	15,5 -0,3 /+0,5	93,0	701	0,272
STORAFLEX	1	95	17,3 -0,5 /+0,8	103,8	913	0,206
STORAFLEX	1	120	19,6 -0,5 /+0,8	117,6	1154	0,161
STORAFLEX	1	150	21,7 -0,5 /+0,8	130,2	1406	0,129
STORAFLEX	1	185	23,9 -0,5 /+0,8	143,4	1747	0,106
STORAFLEX	1	240	27,0 -0,5 /+0,8	162,0	2270	0,0801

(*) Bare Class 5 conductors based on IEC 60228

CURRENT RATINGS

Apply to IEC 60364-5-52 according to installation method type.

Based on at 30 °C Ambient temperature and cable operating temperature 90 °C

For installation in air reference method F refer to Table B.52.12

For direct burial reference method D1 or D2 refer to Table B.52.3, Table B.52.5

For correction factor for ambient temperature Table B.52.14

For group reduction factors for method F refer to Table B.52.21 and Table B.52.17

For Direct Burial Method D2 refer to Table B.52.18 and for Method D1 refer to Table B.52.19

Soil resistivity correction factors for cables buried in ground refer to Table B.52.16



Customer:

Solen Kablo San. Tic. A.Ş.
Arap Cami Mah. Arapkayyum Sok.
Karavelioğlu Han No.23 / 5
Beyoğlu - 34420 İstanbul - Türkiye

All data given here is informative and subject to change.

© Solen Kablo, Türkiye 2024
www.solenkablo.com

Date: